HONGCHEN METAL
INDUSTRIAL METAL MATERIALS

PRODUCT DATA SHEET
Phone / WhatsApp: +86 15052357278
Email: juniper@hongchen-steel.com

PRODUCT SPECIFICATIONS · BAR

Stainless Steel 254 SMO Round Bar

Chemical composition, mechanical properties and material characteristics

Features

- The types and contents of chemical elements in 254SMO stainless steel have been precisely proportioned and optimized, giving it excellent corrosion resistance, high temperature strength and processing performance.
- Therefore, it has been widely used in petroleum, chemical industry, marine engineering and other fields.

Typical Applications

- Used for chemical process equipment, coastal and marine atmospheres, food / pharmaceutical contact surfaces, heat exchangers, tanks and piping. Grade choice should follow the actual medium, chloride level, temperature and whether welded components remain in corrosive service.

Product Parameters

Product Name	254SMO Stainless Steel Bar
Type	Corrosion-Resistant Alloy / Stainless Steel
Standard	ASTM, AISI, JIS, GB, DIN, EN, etc.
Surface	Black, Bright Polished, Rough Turning, Mattness Surface Treatment, No. 4. BA, etc.
Delivery Condition	Annealed / solution annealed; other tempers available by agreement.
Scope of Application	Used for chemical process equipment, coastal and marine atmospheres, food / pharmaceutical contact surfaces, heat exchangers, tanks and piping. Grade choice should follow the actual medium, chloride level, temperature and whether welded components remain in corrosive service.
Certificate	ISO / SGS / BV and EN 10204 3.1 MTC available; third-party inspection and PMI can be arranged per purchase order.
Production Technology	Hot rolling or cold rolling / drawing according to product form; solution treatment and pickling / passivation applied where corrosion performance or surface quality require it. Hot-rolled, forged or cold-drawn routes depending on size; cut-to-length available.
Edge Processing	Cut ends as standard; chamfering, deburring, peeling or centerless grinding available on request.
Outer Diameter	Round Bar
Hexagon Bar	18mm-57mm (11/16″ to 2-3/4″)
Square Bar	18mm-47mm (11/16″ to 1-3/4″)
Flat Steel	1/2 "to 10", Thickness: 2mm-150mm, Can provide customized
Length	1-6 meters, Length can be customized

Chemical Composition

C	Si	Mn	Cr	Ni	Mo	S	P
≤ 0.02	≤ 0.8	≤ 1.0	19.5 ~ 20.5	17.5 ~ 18.5	6.0 ~ 6.5	≤ 0.01	≤ 0.03

Mechanical Properties

Tensile Strength Kb (MPa)	Yield Strength σ0.2 (MPa)	Elongation D5 (%)	Hardness
≥680	≥300	≥45	≤180HRB

Physical Performance

Density(g/cm³)	Modulus of Elasticity(Gpa)	Coefficient of Thermal Expansion(10 -6 /°C)	Coefficient of Thermal Conductivity(W/m * K)	Resistivity(MΩ. cm)
8.0	195	16.0	14.0	85

Selection note: match grade to medium, temperature, chloride level and whether as-welded corrosion service is required.

Related Properties

Corrosion Resistance	Provides practical corrosion resistance in atmospheric exposure, fresh water, food-contact environments and many mild chemical media. Resistance drops when chlorides, reducing acids or high-temperature concentrated solutions become dominant—match the grade to the real medium, temperature and oxygen level.
Formability	Most austenitic corrosion grades form well by bending, rolling, deep drawing and stamping when tooling radii, lubrication and springback are set for the thickness and temper. Work hardening raises strength during cold work; intermediate anneal may be needed for severe multi-stage forming.
Weldability	Generally weldable with common fusion processes. For as-welded corrosive service, prefer low-carbon (L) or stabilized grades, control heat input, and specify filler that preserves corrosion resistance in the weld metal and HAZ. Post-weld cleaning and passivation improve finished performance.
Surface & Cleanliness	Final corrosion behavior is strongly affected by surface finish, free iron contamination and weld discoloration. Pickling, passivation or electropolishing after fabrication is often as important as grade selection for sanitary, marine and chemical equipment.
Selection Notes	Use molybdenum-bearing or higher-alloy variants when pitting, crevice attack or stronger chemical media are expected. Confirm product form (plate, tube, bar, wire) and heat-treatment condition against the project specification before ordering.

Material guidance for your next project

Send your grade, size and application requirements to our team.

hongchen-steel.com

© 2026 HongChen Metal. All rights reserved.