HONGCHEN METAL
INDUSTRIAL METAL MATERIALS

PRODUCT DATA SHEET
Phone / WhatsApp: +86 15052357278
Email: juniper@hongchen-steel.com

PRODUCT SPECIFICATIONS · PIPE

Stainless Steel 440C Pipe

Chemical composition, mechanical properties and material characteristics

Features

- 440C stainless steel, as a high carbon martensitic stainless steel, is widely favored for its high strength, moderate corrosion resistance, and good hardness and wear resistance.
- It has the property to achieve the highest strength, hardness and wear resistance of all the stainless alloys after heat treatment.

Typical Applications

- Selected for shafts, valves, fasteners, molds, cutters and CNC-machined parts where machinability, heat-treatment response and wear resistance matter. Rough machine in the softer condition when possible, then harden / age and finish grind for tight tolerances.

Product Parameters

Product Name	440C Stainless Steel Pipe
Type	Precision Machining / Hardenable Stainless Grade
Standard	ASTM, AISI, JIS, GB, DIN , EN, etc.
Surface	Peeled, turned, ground or polished; black / annealed bar and plate also available.
Delivery Condition	Annealed for machining, or quench-tempered / age-hardened to the ordered hardness.
Scope of Application	Selected for shafts, valves, fasteners, molds, cutters and CNC-machined parts where machinability, heat-treatment response and wear resistance matter. Rough machine in the softer condition when possible, then harden / age and finish grind for tight tolerances.
Certificate	EN 10204 3.1 MTC with chemistry and hardness / mechanical results as ordered.
Production Technology	Supplied for CNC turning, milling and drilling; heat treatment (quench-temper or aging) is applied after rough machining when final strength or wear resistance is required. Seamless or welded supply routes depending on size; cut-to-length and end preparation available.
Edge Processing	Plain, beveled or threaded ends available on request; end finishing and length tolerance per order.
Outer diameter	Round Tube
Square Tube	10*10mm-100*100mm
Rectangular Tube	10*20mm-50*100mm
Wall Thickness	0.6mm-6.0mm
Length	1-6 meters, Length can be customized

Chemical Composition

C	Si	Mn	Cr	S	P
0.95～1.20	≤1.0	≤1.0	16.0～18.0	≤ 0.03	≤ 0.04

Mechanical Properties

Tensile Strength Kb (MPa)	Yield Strength σ0.2 (MPa)	Elongation D5 (%)	Hardness
≥560	≥205	≥18	≤250HB

Physical Performance

Density(g/cm³)	Modulus of Elasticity(Gpa)	Coefficient of Thermal Expansion(10 -6 /°C)	Coefficient of Thermal Conductivity(W/m * K)	Resistivity(MΩ. cm)
7 .60	200	10.1	24.2	360

Selection note: leave finishing stock when hardening after rough machining to hold final tolerances.

Related Properties

Machinability	Suitable for CNC turning, milling, drilling and grinding when sharp tooling, stable fixturing and adequate coolant are used. Free-machining or annealed conditions cut more easily; hardened or heavily cold-worked stock needs reduced speed and more frequent tool changes.
Heat-Treatment Response	Martensitic and precipitation-hardening grades can be quench-tempered or age-hardened after rough machining to raise hardness, strength and wear resistance. Final dimensional stability depends on leaving finishing stock for post-heat-treat grinding.
Wear Resistance	Higher carbon content or a correctly hardened condition improves wear resistance for shafts, cutters, molds and sliding parts. Surface treatments (nitriding, coating) can be added when the base hardness alone is not enough.
Formability	Best bent, straightened or cold-formed in the softer annealed condition, then hardened if the finished part needs high strength. Attempting severe forming in the hardened state risks cracking.
Dimensional Control	Distortion during heat treatment and residual stress from heavy machining are the main risks for precision parts. Stress-relief steps, balanced stock removal and final grind after hardening help hold tight tolerances.

Material guidance for your next project

Send your grade, size and application requirements to our team.

hongchen-steel.com

© 2026 HongChen Metal. All rights reserved.