HONGCHEN METAL
INDUSTRIAL METAL MATERIALS

PRODUCT DATA SHEET
Phone / WhatsApp: +86 15052357278
Email: juniper@hongchen-steel.com

PRODUCT SPECIFICATIONS · PLATE

Monel K-500 Plate

Chemical composition, mechanical properties and material characteristics

Features

- Monel K-500 pipe is made of a high-performance nickel-copper alloy that has excellent corrosion resistance and high-temperature strength.
- It is widely put into use in marine engineering, petrochemical industry, aerospace and other fields.

Typical Applications

- Chosen when Monel 400 corrosion resistance is needed together with higher strength from age hardening—pump shafts, fasteners and oil-tool components.

Product Parameters

Product Name	Monel K-500 Plate
Type	Precipitation-Hardened Ni-Cu Alloy (Monel K-500)
Standard	UNS N05500; ASTM B865
Surface	BA, 2B, No.1, No.4, HL, 8K / polished, pickled or passivated as required.
Delivery Condition	Annealed / solution annealed; other tempers available by agreement.
Scope of Application	Chosen when Monel 400 corrosion resistance is needed together with higher strength from age hardening—pump shafts, fasteners and oil-tool components.
Certificate	ISO / SGS / BV and EN 10204 3.1 MTC available; third-party inspection and PMI can be arranged per purchase order.
Production Technology	Hot rolling or cold rolling / drawing according to product form; solution treatment and pickling / passivation applied where corrosion performance or surface quality require it. Cut-to-length, leveling, plasma / waterjet cutting and surface grinding available.
Edge Processing	Mill, slit or trimmed edge; final edge condition confirmed by thickness, width tolerance and downstream welding / forming needs.
Thickness	0.3mm-200mm
Length	2000mm, 2438mm, 3000mm, 5800mm, 6000mm, 12000mm, etc.
Width	40mm-600mm, 1000mm, 1219mm, 1500mm, 1800mm, 2000mm, 2500mm, 3000mm, 3500mm, etc.

Chemical Composition

C	Al	Si	S	Ti	Mn	Fe	Ni	Cu
0.18 max	2.30 - 3.15	0.5 max	0.01 max	0.35 - 0.85	1.5 max	2.0 max	63.0 min	27.0 - 33.0

Mechanical Properties

Tensile Strength (ksi)	0.2% Yield Strength (ksi)	Elongation% in 2 inches
140	100	17

Physical Performance

	Units	Temperature in°C
Density	8.44 g/cm³	Room
Specific Heat	0.1 Kcal/kg.C	21°
Melting Range	1315-1350°C	-
Modulus of Elasticity	179 KN/mm²	Room
Electrical Resistivity	61.5 μΩ.cm	21°
Coefficient of Expansion	13.7 μm/m °C	20 - 100°
Thermal Conductivity	17.2 w/m-° K	21°

Selection note: match grade to medium, temperature, chloride level and whether as-welded corrosion service is required.

Related Properties

Corrosion Resistance	Provides practical corrosion resistance in atmospheric exposure, fresh water, food-contact environments and many mild chemical media. Resistance drops when chlorides, reducing acids or high-temperature concentrated solutions become dominant—match the grade to the real medium, temperature and oxygen level.
Formability	Most austenitic corrosion grades form well by bending, rolling, deep drawing and stamping when tooling radii, lubrication and springback are set for the thickness and temper. Work hardening raises strength during cold work; intermediate anneal may be needed for severe multi-stage forming.
Weldability	Generally weldable with common fusion processes. For as-welded corrosive service, prefer low-carbon (L) or stabilized grades, control heat input, and specify filler that preserves corrosion resistance in the weld metal and HAZ. Post-weld cleaning and passivation improve finished performance.
Surface & Cleanliness	Final corrosion behavior is strongly affected by surface finish, free iron contamination and weld discoloration. Pickling, passivation or electropolishing after fabrication is often as important as grade selection for sanitary, marine and chemical equipment.
Selection Notes	Use molybdenum-bearing or higher-alloy variants when pitting, crevice attack or stronger chemical media are expected. Confirm product form (plate, tube, bar, wire) and heat-treatment condition against the project specification before ordering.

Material guidance for your next project

Send your grade, size and application requirements to our team.

hongchen-steel.com

© 2026 HongChen Metal. All rights reserved.